

## PRODUCT DATA SHEET

# SUMERU SUPER 401

### **Product Description:**

Sumeru Super 401 is polymer modified tile adhesive for fixing all type of tiles on internal & external floor & ceramic, mosaic and porous stone on wall in interior.

C1T classified according to EN 12004

### **Area of Application:**

- Wall & Floors
- Interior
- Dry area
- Wet Area
- Shower

### **Features & Benefit:**

- High Bonding Strength
- Good Pot Life
- Excellent Workability & Self-curing
- Water Resistant & Easy Mixing
- Ready to use with less material wastage
- Save Time & water
- Eco friendly

### **Surface Preparation:**

All supporting surfaces shall be structurally sound, solid, stable, dry completely and cured well. They shall be clean and free of oil, dust, grease, paint, tar, wax, primers, sealers, curing agent, release agent or any deleterious substance and debris which may prevent or reduce adhesion. Repair all structural, fractionizing & perimeter joints present in the surfaces.

### **Mixing Method:**

Add Sumeru Super 401 to clean water mix thoroughly until lump free mortar is obtained. A bag of 20 kg of Sumeru Super 401 will require approx. 5-6 litres of water to obtain lump free consistency. The adhesive is immediately ready for use. Where mixing by weight is not possible, volume mixing can be carried out at site in the ratio of 26 -28% or (1 water: 3 powder) of water by volume of material. Do not attempt to extend the pot life by adding more water to the mix.

### **Application Method:**

Use suitable notch trowel for required thickness of Sumeru Super 401 adhesive. Choose a typical notched trowel with sufficient depth to achieve > 80% of mortar contact to both tile and substrate for all interior applications & >90% for exterior applications. Leave no voids behind tiles, with pressure, apply a coat by using the trowel's flat side to key mortar into substrate.

If adhesive is skinned over (not sticky) remove and replace with fresh adhesive or premix.

Limitation of application Sumeru Super 401 shall not be applied in the following cases: On metal surfaces and wood.

*Unique and Simple Solution*

**SUMERU**<sup>TM</sup>

**SUPER 401**

# PRODUCT DATA SHEET

## SUMERU SUPER 401

### Precautions:

- Keep out of reach of children.
- Wear suitable protective clothing, gloves and eyes/face protection.
- In case of contact with eyes rinse immediately with plenty of clean water and seek medical advice.
- For more details please refer the relevant Material Safety Data Sheet.

### Technical Information:

**Standards:** C1T, EN-12004, IS-15477; 2004 type 1

Chemical Base: Selective polymer water retention additives, best quality aggregates, standard Portland cement. Tensile Adhesion after 28 days (test method EN 1348).

Test Value	Value	Requirement
Tensile Adhesion Dry	1.0 N/mm <sup>2</sup>	>0.5 N/mm <sup>2</sup>
Tensile Adhesion Wet	0.9 N/mm <sup>2</sup>	>0.5 N/mm <sup>2</sup>
Tensile Adhesion Heat	0.7 N/mm <sup>2</sup>	>0.5 N/mm <sup>2</sup>

Shear adhesion after 28 days test method IS= 15477 type 1 adhesive.

Test Value	Value	Requirement
Shear Adhesion (24 Hours)	2.75-3.00KN	2.5KN
Shear Adhesion Dry (14 days)	8.25-8.50KN	8KN
Shear Adhesion Heat (7 days)	4.50-5.00KN	4KN
Shear Adhesion Wet (7 days)	4.50-5.00KN	4KN

### Physical Properties

Properties	Test values as per specifications
Bulk density	1.30 – 1.35 g/cc (Is 15477 Type 1 adhesive)
Coverage	25 to 30 sq. ft. (5 mm thickness)
Layer thickness	From 3 to 10 mm
Setting time (final)	24 hours (+25 C°)
Foot traffic/grouting of joint wall	4-6 hours (+25 C°)
Foot traffic/grouting of joint floor	24 hours (+25 C°)
Adjustable Time	>35 min (+25 C°)
Slip Resistance	< 0.5 mm (EN 1308)
Pot Life	3-4 hours (+25 C°)
Open Time	>20 min (+25 C°)

*Unique and Simple Solution*

**SUMERU**<sup>TM</sup>

**SUPER 401**

# PRODUCT DATA SHEET

## SUMERU SUPER 401

**Colour:** Grey powder

**Packing:** 20kg

**Shelf life:**

Sumeru Super 401 have 12 months of shelf life from the date of manufacturing.

**Storage Condition:**

Store sealed bag of Sumeru Super 401 in cool & dry condition. Protect from direct sunlight & frost.

**Cleaning of Tools:**

Tools and containers may be cleaned using clean water when the adhesive is still fresh in other case the hardened adhesive can be removed from mechanical tools.

**Health & Safety measures:**

For more information and guidance of safety, storage and disposal of chemical products, customers should refer to the updated data sheet of the product which contains all the details of physical toxicological, ecological and other safety related data.

**Important Notes:**

The information and in particular, the recommendations relating to the application and end-use of Sumeru products, are given in good faith based on Sumeru's current knowledge and experience. The user of the product must test product's suitability for the intended application and purpose.

Sumeru reserves the right to change the properties of its products. Users must always refer to the most issue of the local product data sheet for the product concerned, copies of which will be supplied on request.

**Address:** 77-78, Pushkar Industrial & Logistics Park,  
B/h. Satyam Mall, Nr. Shivam – 4,  
Sarkhej Bavla Road, Changodar,  
Ahmedabad-382210.

Helpline Number : 09512909819  
E-mail : [sumeru.us@gmail.com](mailto:sumeru.us@gmail.com)



**Unique and Simple Solution**

**SUMERU™**

**SUPER 401**