

PRODUCT DATA SHEET

SUMERU STONE MASTER 609

Product Description:

Sumeru Stone Master 609 is high performance polymer modified high strength non-slip tile and stone adhesive for fixing all type of fully vitrified tiles & glass mosaic, natural stones, engineered stone, marble, granite, low porosity tiles & stones on floor & cladding on wall for interior and exterior.

C2TE classified according to EN 12004 and IS 15477:2019 Type 3T.

Area of Application:

- Wall & Floors
- Interior & Exterior
- Brick Masonry
- Cement Mortar bed
- Dry areas
- Wet Areas
- Showers
- Trimix Concrete
- Swimming Pools
- Tile on Tile

Features & Benefit:

- Flexible and high strength adhesive for natural stones.
- Cladding, swimming pools, industrial and heavy trafficked floors in indoor and outdoor situation.
- Slip resistant for vertical application.
- Excellent Workability.
- Easy mixing & application.
- Ready to use

Surface Preparation:

All supporting surfaces shall be structurally sound, solid, stable, dry completely and cured well. They shall be clean and free of oil, dust, grease, paint, tar, wax, primers, sealers, curing agent, release agent or any deleterious substance and debris which may prevent or reduce adhesion. Repair all structural, fractionizing & perimeter joints present in the surfaces.

Mixing Method:

Add Sumeru Stone Master 609 to clean water mix thoroughly until lump free mortar is obtained. The adhesive is immediately ready for use. Where mixing by weight is not possible, volume mixing can be carried out at site in the ratio of 22% -26% or (1 water: 4 powder) of water by volume of material. Do not attempt to extend the pot life by adding more water to the mix.

Application Method:

Using a suitable square notch trowel. Choose a typical notched trowel with sufficient depth to achieve > 80%. Mortar Contact to both tile and substrate for all interior applications and >90% for exterior installations. Leave no voids behind tiles, with pressure, apply a coat by using the trowels flat side to key mortar into substrate. If adhesive is skinned over (not sticky) remove and replace with fresh adhesive or premix.

Unique and Simple Solution

SUMERUTM

STONE MASTER 609

PRODUCT DATA SHEET

SUMERU STONE MASTER 609

Limitation of application Sumeru Stone Master 609 shall not be applied in the following cases:
On metal surfaces and wood.

Precautions:

- Keep out of reach of children.
- Wear suitable protective clothing, gloves and eyes/face protection.
- In case of contact with eyes rinse immediately with plenty of clean water and seek medical advice.
- For more details please refer the relevant Material Safety Data Sheet.

Technical Information:

Standards: C2TE, EN-12004, IS-15477: 2019 Type 3T

Chemical Base: Selective polymer water retention additives, best quality aggregates, standard Portland cement. Tensile Adhesion after 28 days (test - method EN 1348)

Test Value	Value Grey	Value White	Requirement
Tensile Adhesion Dry	2.1 N/mm ²	1.9 N/mm ²	≥1.0 N/mm ²
Tensile Adhesion Wet	1.6 N/mm ²	1.6 N/mm ²	≥1.0 N/mm ²
Tensile Adhesion Heat	1.4 N/mm ²	1.3 N/mm ²	≥1.0 N/mm ²

Shear adhesion after 28 days test method IS= 15477 Type 3T adhesive.

Test Value	Value	Requirement
Shear Adhesion (24 Hours)	5.50-6.50 KN	4KN
Shear Adhesion Dry (14 days)	10.50-11.50KN	10KN
Shear Adhesion Heat (7 days)	5.50-6.50KN	5KN
Shear Adhesion Wet (7 days)	5.50-6.50KN	5KN

Physical Properties

Bulk density	1.30 – 1.35 g/cc (Is 15477 Type 3T adhesive)
Coverage	50 to 60 sq. ft. (5 mm thickness)
Layer thickness	From 3 to 15 mm
Setting time (final)	24 hours (+25 C°)
Foot traffic/grouting of joint wall	4-6 hours (+25 C°)
Foot traffic/grouting of joint floor	24 hours (+25 C°)
Adjustable Time	>35 min (+25 C°)
Slip Resistance	< 0.5 mm (EN 1308)
Pot Life	3-4 hours (+25 C°)
Open Time	>30 min (+25 C°)

Unique and Simple Solution

SUMERU™

STONE MASTER 609

PRODUCT DATA SHEET

SUMERU STONE MASTER 609

Colour: Grey & White powder

Packing: 40kg

Shelf life:

Sumeru Stone Master 609 have 12 months of shelf life from the date of manufacturing.

Storage Condition:

Store sealed bag of Sumeru Stone Master 609 in cool & dry condition. Protect from direct sunlight & frost.

Cleaning of Tools:

Tools and containers may be cleaned using clean water when the adhesive is still fresh in other case the hardened adhesive can be removed from mechanical tools.

Health & Safety measures:

For more information and guidance of safety, storage and disposal of chemical products, customers should refer to the updated data sheet of the product which contains all the details of physical toxicological, ecological and other safety related data.

Important Notes:

The information and in particular, the recommendations relating to the application and end-use of Sumeru products, are given in good faith based on Sumeru's current knowledge and experience. The user of the product must test product's suitability for the intended application and purpose.

Sumeru reserves the right to change the properties of its products. Users must always refer to the most issue of the local product data sheet for the product concerned, copies of which will be supplied on request.

Address: F1-104, Jhanjira CHS Ltd, Sarova Complex,
Thakur Village Road, Samta Nagar,
Kandivali (E), Mumbai-400101.

Helpline Number : +91 91371 42270

E-mail : office@sumeruuss.com



Unique and Simple Solution

SUMERU™